

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

(11) Publication number:

**0 283 224**  
**A1**

(12)

# EUROPEAN PATENT APPLICATION

(21) Application number: 88302192.5

(51) Int. Cl.<sup>4</sup> **B01D 53/36**, **B01J 35/04**,  
**F01N 3/28**, **C04B 38/00**

(22) Date of filing: 14.03.88

(30) Priority: 16.03.87 JP 37125/87

(43) Date of publication of application:  
21.09.88 Bulletin 88/38

(84) Designated Contracting States:  
BE DE FR GB


(71) Applicant: NGK INSULATORS, LTD.  
2-56, Suda-cho, Mizuho-ku  
Nagoya City Aichi Pref.(JP)

(72) Inventor: Mizutani, Isao  
12 Shiota-Cho 1-Chome Minami-Ku  
Nagoya City Aichi Pref.(JP)  
Inventor: Hijikata, Toshihiko  
1607, Kamisawa 2-Chome Midori-Ku  
Nagoya City Aichi Pref.(JP)  
Inventor: Harada, Takashi  
32 NGK Kita-Kazoku Apart. 9, Takada-Cho  
3-Chome  
Mizuho-Ku Nagoya City Aichi Pref.(JP)

(74) Representative: Paget, Hugh Charles Edward  
et al  
MEWBURN ELLIS & CO. 2/3 Cursitor Street  
London EC4A 1BQ(GB)

(54) Ceramic honeycomb structural bodies and method of producing the same.

(57) A ceramic honeycomb structural body having many through-holes (4) surrounded by partition walls (2) is made by extrusion. To improve the dimensional accuracy of the finished body, a coating layer (5) is formed on the outer peripheral wall (3) of the main ceramic honeycomb structural body which has an outer diameter smaller than a predetermined dimension. The coating layer (5) brings the outer diameter of the structural body into the desired dimensional tolerance.



EP 0 283 224 A1

CERAMIC HONEYCOMB STRUCTURAL BODIES AND METHOD OF PRODUCING THE SAME

This invention relates to a ceramic honeycomb structural body useful for example as a catalyst carrier for purification of an exhaust gas from internal combustion engine for automobiles, a diesel particulate filter (hereinafter referred to as DPF), or a catalyst carrier for purification and/or deodorization of exhaust gas using various gases or petroleum as a fuel and a method of producing the same.

Recently, catalyst converters have been used for the purification of exhaust gas from an internal engine in connection with the prevention of air pollution. In general, the catalyst converter is manufactured by coating a honeycomb structural carrier of cordierite ceramic with an active substance having a large specific surface area such as  $\gamma$ -alumina and carrying a noble metal catalyst such as platinum, palladium, rhodium or the like on the  $\gamma$ -alumina layer to form a honeycomb structural catalyst carrier, and airtightly inserting this carrier into a casing made from stainless steel or the like through a sealing member, and arranged in a passage for the exhaust gas discharged from the internal engine, at where hydrocarbon, carbon monoxide, nitrogen oxide and the like included in the exhaust gas are reduced and purified on the catalyst bed of the honeycomb structural carrier.

Such a ceramic honeycomb structural carrier is manufactured through extrusion molding, drying and firing steps, but inevitable size error and deformation occur in the ceramic honeycomb structure at each step. Firstly, the extrusion molded product contains water, binder and the like and is very soft at the extrusion molding step, so that it easily deforms under its dead weight. In large products of 300 mm in diameter, for example, if they are extruded in a direction perpendicular to gravity, cells existing in the outer peripheral portion of the product break under the dead weight of the product, while if they are extruded in a direction parallel to gravity, the lower portion of the product buckles under its dead weight. Secondly, the drying and/or firing of the extrusion molded product cannot be carried out completely and uniformly at the drying and firing steps, so that there is caused the scattering of shrinkage in various portions of a final product. Therefore, the final product has a drawback that the accuracy of outer diameter is somewhat poor and also the cylindricity is poor.

It is, therefore, an object of the invention to provide a ceramic honeycomb structural body having predetermined outer dimension or dimensions and accuracy of shape.

According to a first aspect of the invention, there is provided a ceramic honeycomb structural

body having many through-holes surrounded by partition walls, comprising a main ceramic honeycomb structural body made through extrusion molding and having an outer diameter smaller than a predetermined dimension, and a coating layer formed on the outer peripheral wall of the main body so as to bring the outer diameter into the predetermined dimensional tolerance.

According to a second aspect of the invention, there is provided a method of producing a ceramic honeycomb structural body, which comprises the steps of:

- a) extrusion-molding a main ceramic honeycomb structural body having many through-holes;
- b) applying ceramic material onto the outer peripheral wall of the main body to form a coating layer thereon so as to bring the outer diameter into a predetermined dimensional tolerance; and
- c) firing the resulting coated main body.

According to a third aspect of the invention, there is provided a method of producing a ceramic honeycomb structural body, which comprises the steps of:

- a) extrusion-molding a main ceramic honeycomb structural body having many through-holes;
- b) firing the main body; and
- c) applying ceramic material onto the outer peripheral wall of the fired main body to form a coating layer thereon so as to bring the outer diameter into a predetermined dimensional tolerance.

The invention will be explained with reference to the accompanying drawing, wherein:

The figure is a perspective view of an embodiment of the ceramic honeycomb structural body according to the invention.

According to the invention, the coating layer compensating the difference between the predetermined dimensional tolerance and the actual outer diameter of the main ceramic honeycomb structural body is locally or wholly arranged onto the outer peripheral wall of the main body having an outer diameter smaller than the predetermined dimension, whereby not only the outer peripheral wall is reinforced but also the outer diameter thereof can be corrected into a predetermined dimensional tolerance.

Heretofore, when the ceramic honeycomb structural body is airtightly inserted into a casing for the catalyst carrier or DPF in the internal engine through a sealing member or a cushioning member for preventing gas leakage and damping vibrations, if the dimensional accuracy of the ceramic hon-

eycomb structural body is poor, there have been adopted some countermeasures for compensating a difference between the actual size and the predetermined dimensional tolerance of the structural body, such as change of thickness in the sealing or cushioning member, use of thickened sealing or cushioning member and the like for putting the sealing or cushioning member within a constant surface pressure range. However, according to the invention, the dimensional accuracy of the structural body is good as mentioned above, so that a relatively thin sealing or cushioning member having a constant thickness can be used and the economical merit becomes good.

Furthermore, when the ceramic honeycomb structural main body is formed by extrusion molding, wavy fine unevenness is generally produced on the outer peripheral wall of the main body in the extrusion direction. According to the invention, such a fine unevenness is buried with the coating layer to thereby make the surface of the main body smooth and consequently the performance for sealing gas is considerably improved.

The invention will be illustrated by the following embodiment.

As shown in the single figure, a ceramic honeycomb structural body 1 is obtained by extrusion-molding a cordierite material and comprises partition walls 2, an outer peripheral wall 3 and through-holes 4 defined by the partition walls 2. The sectional form of the through-hole 4 is square in the illustrated embodiment but may take an arbitrary form such as polygonal form, e.g. hexagon or the like, circle, and ellipsoid. Moreover, the term "through-hole" used herein includes a case that an end of the through-hole is plugged as in DPF.

The ceramic honeycomb structural body 1 according to the invention is provided with a coating layer 5 after the drying or firing as described in the following examples. (In the single figure is exaggeratedly shown the coating layer.)

#### Example 1

A cordierite material was extrusion-molded and dried to obtain a ceramic honeycomb structural main body having a rib thickness of 0.3 mm, a cell density of 48.5 cells/cm<sup>2</sup>, a maximum outer diameter of 102 mm, a whole length of 103 mm and a roundness of 0.7 mm. Then, the main body was placed in a cylinder having an inner diameter of 103±0.1 mm and a height of 103 mm, and a cordierite slurry was poured into a space between the outer peripheral surface of the main body and the inner peripheral surface of the cylinder and dried to form a dried honeycomb structural body having a maximum outer diameter of 102.5 mm, a

whole length of 103 mm and a roundness of 0.1 mm. Next, the dried body was fired at 1,300~1,470°C to obtain a ceramic honeycomb structural body having a maximum outer diameter of 99.9 mm, a whole length of 100 mm and a roundness of 0.4 mm. In this ceramic honeycomb structural body, fine unevenness was not observed in the outer peripheral wall thereof.

#### Example 2

The same procedure as in Example 1 was repeated to obtain a ceramic honeycomb structural main body having a rib thickness of 0.17 mm, a cell density of 82 cells/cm<sup>2</sup>, a maximum outer diameter of 99 mm, a whole length of 100 mm and a roundness of 0.8 mm. Then, this main body was fired and placed in a cylinder having an inner diameter of 101±0.1 mm and a height of 100 mm, and a cordierite slurry was poured and dried to obtain a ceramic honeycomb structural body having a maximum outer diameter of 100.1 mm and a roundness of 0.2 mm. The fine unevenness was not observed in the outer peripheral wall of the structural body.

In order to measure the mechanical strength of the resulting ceramic honeycomb structural body, aluminum plates of 100 mm in diameter and 20 mm in thickness were fitted to upper and lower end faces of the structural body and the side face of the structural body was air-tightly enclosed with a urethane sheet of 0.5 mm in thickness, which was placed in a pressure vessel filled with water. Then, a pressure inside the vessel was gradually raised to measure a pressure value producing a sound of destruction (known as "isostatic strength"). In the ceramic honeycomb structural body of Example 2, the pressure value was 30 kgf/cm<sup>2</sup>, which was improved by about two times as compared with the ceramic honeycomb structural body having no coating layer (whose pressure value was 13 kgf/cm<sup>2</sup>).

#### Example 3

To the same fired cordierite honeycomb structural body as in Example 2 was applied a mortar of alumina cement, which was then dried and machined to obtain a ceramic honeycomb structural body having a maximum outer diameter of 100 mm and a roundness of 0.1 mm.

#### Example 4

A large fired cordierite honeycomb structural body for DPF having a rib thickness of 0.43 mm, a cell density of 15.5 cells/cm<sup>2</sup>, an upper maximum outer diameter of 298 mm, a lower maximum outer diameter of 302 mm, a whole length of 355 mm and a roundness of 4.1 mm was coated with a mortar of alumina cement so as to render the outer diameter into about 310 mm and dried to obtain a dried product having an outer diameter of 305±0.3 mm. The dried product was machined to obtain a ceramic honeycomb structural body having roundnesses at upper and lower portions of 0.2 mm and 0.4 mm, respectively.

As described in the above example, in order to obtain products having a good outer diameter, roundness or profile of a surface, it is preferable that the ceramic honeycomb structural main body is previously produced at a size smaller than the predetermined dimensional tolerance and then the coating layer is provided at the outer peripheral portion of the main body so as to put the outer diameter into the predetermined dimensional tolerance. As the material for the coating layer, it is favorable to use the same material as in the main body or a material containing a small amount of the same material as in the main body and having a thermal expansion coefficient similar to that of the main body. Furthermore, it is preferable to conduct the coating after the firing from a viewpoint of dimensional accuracy and cost, but the coating layer may be peeled off from the ceramic honeycomb structural main body when thermal shock is strong because the main body is not integrally united with the coating layer. On the other hand, when the main body is coated with the coating material and then fired, the peeling is not caused through thermal shock, but the main body is apt to be subjected to a deformation during the firing and consequently the dimensional accuracy of the resulting ceramic honeycomb structural body is somewhat poor. When the fired body is refired after the coating, the peeling is not caused and the dimensional accuracy is good, but the cost becomes undesirably high. Therefore, it is necessary to select the above three coating methods in accordance with the use purpose.

Although the invention has been described with respect to the above examples, it may be subjected to various modifications and changes without departing from the scope of the invention. For instance, the structural body is cylindrical in the illustrated embodiment but may be ellipsoidal or the like. As the ceramic material, other ceramic materials may be used in addition to the cordierite. The coating layer is not necessarily formed over the whole periphery of the main body and may be

formed only to a portion of the main body. Moreover, the coating layer may be formed before or after the catalyst is deposited on the main body.

As mentioned above, according to the invention, the ceramic honeycomb structural body has predetermined outer diameter and cylindricity and is good in the dimensional accuracy, so that when this structural body is applied to a catalyst apparatus for exhaust gas, an apparatus for purification of exhaust gas and the like, a relatively thin sealing member having a constant thickness can be used, which becomes economical. Furthermore, fine unevenness produced on the outer peripheral wall of the main body at the extrusion molding step is buried with the coating layer to make the surface of the structural body smooth, whereby the performance for sealing gas is improved.

#### Claims

1. A ceramic honeycomb structural body having many through-holes surrounded by partition walls, comprising a main ceramic honeycomb structural body made through extrusion molding and having an outer dimension smaller than a predetermined dimension, and a coating layer formed on the outer peripheral wall of the main body so as to bring said outer diameter into a predetermined dimensional tolerance.

2. The ceramic honeycomb structural body according to claim 1, wherein said coating layer has a thermal expansion coefficient equal to that of said main ceramic honeycomb structural body.

3. A method of producing a ceramic honeycomb structural body, which comprises the steps of:

a) extrusion-molding a main ceramic honeycomb structural body having many through-holes;

b) applying a ceramic material onto the outer peripheral wall of the main body to form a coating layer thereon so as to bring an outer dimension into a predetermined dimensional tolerance; and

c) firing the resulting coated main body.

4. A method of producing a ceramic honeycomb structural body, which comprises the steps of:

a) extrusion-molding a main ceramic honeycomb structural body having many through-holes;

b) firing the main body; and

c) applying a ceramic material onto the outer peripheral wall of the fired main body to form a coating layer thereon so as to bring an outer dimension into a predetermined dimensional tolerance.

5. The method according to claim 3 or 4, wherein said ceramic material is applied after said main ceramic honeycomb structural body is placed in a cylinder having a predetermined inner diameter.

5

6. The method according to claim 3 or 4, wherein said ceramic material has a thermal expansion coefficient equal to that of said main ceramic honeycomb structural body.

7. The method according to claim 4, wherein said coating layer is further subjected to a firing treatment.

10

8. The method according to claim 4, wherein said coating layer is further matured.

15

20

25

30

35

40


45

50

55

5

BEST AVAILABLE COPY



BEST AVAILABLE COPY



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number

EP 88 30 2192

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
A	US-A-3 938 232 (F. NODA) * Figures 1,2; column 2, line 33 - column 3, line 35 * ---	1,3,5,7	B 01 D 53/36 B 01 J 35/04 F 01 N 3/28 C 04 B 38/00
A	US-A-3 876 556 (E. LAACK) * Figures 1-3; column 1, lines 39-48; column 3, line 15 - column 4, line 4 * ---	1,2	
A	US-A-4 285 909 (S. MIZUSAWA) -----		
			TECHNICAL FIELDS SEARCHED (Int. Cl. 4)
			B 01 D B 01 J F 01 N C 04 B
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 17-06-1988	Examiner BOGAERTS M. L. M.
<b>CATEGORY OF CITED DOCUMENTS</b> X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document  T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons  & : member of the same patent family, corresponding document			

EPO FORM 1503 (04/87) (P0401)

BEST AVAILABLE COPY